

TECHNICAL SHEET



NO.	TEST METHOD	TEST DESCRIPTION	TEST VALUE
1	ASTM D7032-17 Section 4.2 &	Flexural strength and Modulus of elasticity	Flexural Strength : 27.4MPa
	ASTM D6109-13 Method A	DKG5.5/1 (Platinum Decking)	Modulus of Elasticity: 4192MPa
2	ASTM D1761-20	Screw withdrawal test	5510N
3	ASTM E831-25	Mean coefficient of linear thermal expansion	-30°C ~ 30°C: 41.9µm/(m.°C)
			30°C ~ 70°C: 46.5µm/(m.°C)
4	ASTM D2395-17 Method B mode (III)	Specific gravity	1.532
5	ISO 62:2008 Method 1	Water absorption	6h : 2.03%
			32h : 3.00%
			124h : 4.05%
6	ASTM D648-18 Method B	Deflection temperature under load	71.1°C
7	ASTM E84-23d	Standard Test Method for Surface Burning Characteristics of Building Materials - (B)	Flame Spread Index (FSI): 0
			Smoke-Developed Index: 400
			Class A Interior Wall & Ceiling Finish Category (FSI: 0-25, SDI 0-450)
8	BS 476-4:1970+CORR-2014	Fire test on building materials and structures-Part 4: Non-combustibility test for materials.	Flame continuance(s)
			Specimen 1: 911
			Specimen 2: 892
9	BS 476 Part 6:1989 + A1:2009 + C1:2014	Fire test on building materials and structures Part 6.	Specimen 3: 953
			Fire propagation index, I: 6.7
10	BS 476 Part 7:1997	Incorporating Corrigendum No.1: 2014 Fire tests on building materials and structures Part 7	Class 1
11	CAN/ULC-S102.2:2018+R1:2019	Standard method of test for surface burning characteristics of flooring, floor coverings, and miscellaneous and assemblies.	FSR: 15
			SDC: 265
12	ASTM D2240: Shore D	Hardness test of recycled plastic battens	Average: 88
13	ASTM E303-1993(2008)	Determination of Surface Frictional Properties Using British Pendulum Skid Resistance Tester	Mean BPN
			Parallel to Groove: 55
			Perpendicular to Groove: 71
14	ASTM D3345-17 and AWPA E1-17	Termite test. Durability of EFC (Enhance Fiber Composite) samples against subterranean termites	EFC (Enhance Fiber Composite) sample blocks suffered slight attach up to 3% of cross-sectional area.
15	CEN/TS 15083-2	Durability of wood and wood-based products- Determination of the natural durability of solid wood against wood-destroying fungi, test methods- Part 2: Soft rotting micro-fungi	Very durable against soft rot fungi

16	ASTM C518-21	Thermal conductivity and thermal resistance	Thermal Conductivity: 0.161 W/(m.K) Thermal Resistance: 0.250 h.ft².°F/BTU
17	ASTM D1525	Vicat softening temperature analysis	Standard: 92.0°C
18	ASTM D143-23 Section 12 and client's requirement	Compression perpendicular to grain	Compressive stress at 10% deformation: 42.3MPa
19	ASTM D143-23 Section 14 and client's requirement	Shear strength (Perpendicular to the L direction)	12175N
20	ASTM D143-23 Section 14 and client's requirement	Shear strength (Parallel to the L direction)	12363N
21	ASTM D2394-17 (2022) Section 33-37	Coefficient of friction	a) Static coefficient of friction
			X direction: 0.79
			Y direction: 0.82
			b) Sliding coefficient of friction
			X direction: 0.67
			Y direction: 0.72
22	ASTM D198-15 Section 21-28 and client's requirement	Compression(parallel to grain)	Compressive strength: 57.5MPa
23	ASTM D198-15 Section 29-36 and client's requirement	Tensile strength	19.9MPa
24	ASTM D2047-17	Standard test method for static coefficient of friction of polish-coated flooring surfaces as measured by the James machine	Dry Condition
			Leather test shoe: 0.54
			Neolite test shoe: 0.52
			Rubber test shoe: 0.79
			Wet Condition
			Leather test shoe: 0.77
			Neolite test shoe: 0.72
			Rubber test shoe: 0.94

Tested 2026

- Attractive aesthetics
- Resistance to the elements
- Low Maintenance
- Versatile style
- Lasting durability
- US-based production
- Proven performance
- True sustainability
- Easy installation



Providing Architects and Builders with
Superior Paving, Decking and Pedestal Products.

Commercial | Luxury Residential | Municipal

Extended Team

We can also provide technical consultation and installation training for projects that involve Buzon Pedestals. Please contact us to discuss your particular needs. HDG Building Materials also has a network of experienced installers in many major cities. Please contact us for introductions or referrals.

Sales Representatives

Sales representatives for HDG Building Materials are located in the Pacific Northwest, Southern California, and Iowa.

Outside of those regions? No problem, we are happy to serve. Please contact us at 503.360.9551



HDG Building Materials is an authorized dealer for Novano composite decking and cladding products. HDG provides architectural sales and support in North America.

HDG Building Materials
Commercial | Luxury Residential | Municipal

4508 SE Ascension Drive
Camas, WA 98607

503.360.9551

sales@hdgbuildingmaterials.com